

2000 SERIES

TECHNICAL DATA



Product datasheet Issue No 4 Issued Nov 2004

RA 2320/2325 EURATRANS REINFORCED ACRYLIC TRANSFER TAPE

2320 on std. 76mm cores, 2325 on 25mm dispenser cores

TECHNICAL DETAILS

TYPICAL VALUE

UNITS

Thickness, adhesive + carrier	0.060	mm
Release liner thickness	0.055	mm
180 degree peel adhesion: Open side	700	N/m
Closed side	700	N/m
Polyester loop tack: Open side	500	N/m
Closed side	500	N/m
Liner release	10	N/m
Service temperature	-10 to +100	Deg. C.
pH of water extract	7.0 - 7.5 *	
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	30	Hours
Shelf life	12	Months

Test Methods: BS 7116
*Test Method BS EN 60454-2

.THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY
ALL DATA IS BASED UPON AVERAGE VALUES THE PURCHASER SHALL BE RESPONSIBLE FOR
.DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES